





Test Report SL92419306794001FW Date:June 26,2024 Page 1 of 6

Applicant: CORTINA NV

MEERSBLOEM- MELDEN 42, 9700 OUDENAARDE, BELGIUM

Attn: Peter De Mezure

The following products were identified on behalf of the client as:

Group Reference : BESTRUN MF EH (BSTRUNMFEH)

BESTBOY MF EH (BSTBOYMFEH)

Model(s) Description : BESTRUN MF EH (BSTRUNMFEH) Safety Low shoes in Black

BESTBOY MF EH (BSTBOYMFEH) Safety Ankle Boot in Black

The following sample(s) was/were submitted for testing:

Sample Description : Three Pairs of Low Shoe in Black

Buyer's Name : CORTINA

Brand : SAFETY JOGGER

Manufacturer : CORTINA Size : Men's US9

Model Name : BESTRUN MF EH (BSTRUNMFEH)

Toecap : SJ Composite Toecap ZL604 Puncture Resistant Device : SJ FLEX Composite Insert EH

Sole : Black PU Midsole + Grey PU Outsole

Upper : Black Embossed Cow Leather

Collar : Black Best PU
Tongue : Black Best PU

Tongue Lining : Blue Polyester SJ BK Mesh
Vamp Lining : White Polyester Non-Woven
Quarter Lining : Grey Polyester SJ BK Mesh
Counter Lining : Grey Polyester SJ BK Mesh
Insole : SJ FLEX Composite Insert EH

In-sock (foot-bed) : Dark Grey Polyester Mesh + SJ FOAM3 Industrial (PU)

Standard : ASTM F2413-18/ASTM F3445-21

Test Performance/ : See Testing Results Page

Standard

Sample Receiving Date : Jun 20, 2024

Testing Period : Jun 20, 2024 ~ Jun 26, 2024

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN. Doccheck@gss.com

No.198, Kerbu Road, Science Chy, Economic & Technological Development Area, Guangahou, Guangdong, China 510663 t (86-20) 82155555 f (86-20) 82075169 www.sgsgroup.com.cn 中国・广东・广州高新技术产业开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075169 sgs.china@sgs.com







SL92419306794001FW

Date:June 26,2024 Page 2 of 6

Signed for and on behalf of SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Asan Huang(Approved Signatory)

SGS does not verify authenticity of any Brand/Trademark of products. Buyers must check if the product is genuine with the Brand/Trademark owner directly.

Conclusion	A US 9#	Remark
Compression Resistance	Р	
Electric Hazard Resistance	Р	
Slip Resistance	Р	

Remark(s): P = Meet Client's Requirement.

F = Below Client's Requirement. # = No Specified Requirement.

NA = Not Applicable.









SL92419306794001FW

Date:June 26,2024 Page 3 of 6

Test Result

Compression Resistance

(ASTM F2412-18a, Clause 6; Compression load: 2500 lbf)

A US 9#(Left)

A 55 on (Lott)			
	No. 1	Requirement	
Internal Height Clearance(mm)	24.6	Min. 12.7 mm	

Conclusion

Pass

A US 9#(Right)

	No. 2	No. 3	Requirement
Internal Height Clearance(mm)	24.5	24.8	Min. 12.7 mm

Conclusion Pass

Electric Hazard Resistance

(ASTM F2412-18a, Clause 9; Test Voltage: 18 kV at 60 Hz; Test Period: 1 min)

A US 9#(Left)

	No. 1	No. 2	Requirement
Leakage Current(mA)	0.3	0.4	Max. 1.0 mA

Conclusion Pass

A US 9#(Right)

71 33 011 (1 tight)			
	No. 3	Requirement	
Leakage Current(mA)	0.3	Max. 1.0 mA	

Conclusion Pass



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction form exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approved of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck-Rogs.com

No.198, Nezhu Noad, Solenes Chy, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663 t (86-20) 82155555 f (86-20) 82075169 www.sgsgroup.com.cn 中国・广东・广州高新技术产业开发区科学城科珠路198号 邮編: 510663 t (86-20) 82155555 f (86-20) 82075169 sgs.china@sgs.com







SL92419306794001FW

Date:June 26,2024 Page 4 of 6

Slip Resistance

(ASTM F2913-19; Lubricant: Distilled Water, Vertical Force: (500±25) N)

A US 9#-shoe 1 (left)	Unit	Forepart	Heel part	Requirement
Clay Tile				
Tested Dry Then Wet				
Coefficient of Friction				-
Dry	-	0.64	0.60	Min.0.40
Wet	-	0.56	0.53	Min.0.40
Conclusion		Pass		
A US 9#-shoe 2 (right)	Unit	Forepart	Heel part	Requirement
Clay Tile				
Tested Wet Then Dry				
Coefficient of Friction				-
Dry	-	0.62	0.59	Min.0.40
Wet	-	0.52	0.52	Min.0.40
Conclusion		Pass		
A US 9#-shoe 3 (left)	Unit	Forepart	Heel part	Requirement
Clay Tile				
Tested Dry Then Wet				
Coefficient of Friction				-
Dry	-	0.65	0.61	Min.0.40
Wet	-	0.53	0.52	Min.0.40
Conclusion		Pass		

Remark:

1) The performance of slip resistance can be affected by surface roughness, presence of water, contaminants such as grease and other foreign materials, and floor surface wear over time.

2) Shoe Size: US 9



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction form exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approved of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck-Rogs.com

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663 t (86-20) 82155555 f (86-20) 82075169 www.sgsgroup.com.cn 中国・广东・广州高新技术产业开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075169 sgs.china@sgs.com







SL92419306794001FW

Date:June 26,2024 Page 5 of 6



Tested sample



The sample has not been tested and provided by the client for reference only. Product information is provided by applicant without verification or authentication of the brand.

Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019.

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction form exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approved of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck-Rogs.com

No.198, Kezhu Road, Science City, Economic & Technological Development Area, Guangzhou, Guangdong, China 510663 t (86-20) 82155555 f (86-20) 82075169 www.sgsgroup.com.cn 中国・广东・广州高新技术产业开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075169 sgs.china@sgs.com







SL92419306794001FW

Date:June 26,2024 Page 6 of 6



Verification: check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction form exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approved of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck-Rogs.com

No.198, Keatru Read, Science City, Economic & Technological Development Area, Guangatrou, Guangdong, China 510663 t (86-20) 82155555 f (86-20) 82075169 www.sgsgroup.com.cn 中国・广东・广州高新技术产业开发区科学城科珠路198号 邮编: 510663 t (86-20)82155555 f (86-20)82075169 sgs.china@sgs.com