



Total Quality. Assured.

## TEST REPORT



中国认可  
国际互认  
检测  
TESTING  
CNAS L0220

Number: GZHT91332070

Date: May 07, 2025

Applicant: CORTINA N.V.  
MEERSBLOEM-MELDEN 42,  
9700 OUDENAARDE, BELGIUM  
Attn: REBECCA/JENNY

### Sample Description:

Three (3) groups of submitted samples said to be:

(A) Two (2) pairs of Men's Occupational Low Shoes in Black

(B) Two (2) pairs of Men's Occupational Boots in Black

(C) Two (2) pairs of Men's Occupational Boots in Beige.

Standard : ASTM F2892-24

Size : US 9

Buyer's Name : CORTINA NV

Ref. No : (A) TACTIC LOW

(B) TACTIC

(C) DUNE

Brand : SAFETY JOGGER

Manufacturer : CORTINA NV

Colour : Black, Beige

Vendor : --

Supplier : --

P.O. No. : --

Ref. : (A) Occupational Low Shoe in Black

(B) Occupational Boot in Black

(C) Occupational Boot in Beige

Country Of Origin : --

Goods Exported To : E.U./U.S.

Date Received/Date Test Started : Apr. 24, 2025

Testing Period : Apr. 24, 2025– May 06, 2025

Date Final Information Confirmed: --

Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at [gzfootwear@intertek.com](mailto:gzfootwear@intertek.com)

Authorized By:  
For Intertek Testing Services Shenzhen Ltd.  
Guangzhou Branch

Guiliang Dong  
Senior Lab Manager



Page 1 Of 5

EC / lynnyang

**Intertek Testing Services Shenzhen Ltd. Guangzhou Branch**  
深圳天祥质量技术服务有限公司广州分公司  
Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou 510730  
广州市黄埔区保盈东路8号401房、501房、601房、801房、901房、1003房  
Tel: +86 20 2820 9114 Postcode: 510730

[www.intertek.com](http://www.intertek.com)

检验检测专用章

SHENZHEN BRANCH

(6)

## Slip Resistant Footwear (SRO) (ASTM F2913-24)

| Conditioning Test Specimen |                  | Test Condition |                                |
|----------------------------|------------------|----------------|--------------------------------|
| Temperature                | (23±2) °C        | Atmosphere     | (23±2) °C, (50±5)% RH          |
| Relative Humidity          | (50±5)% RH       | Test Surface   | Flat Unglazed Clay Quarry Tile |
| Period                     | At Least 3 Hours | Vertical Force | 500 N                          |

(B)

| Size      | Sequence     | Conditions | Modes                  | Results (COF) | ASTM F2892-24 Requirement | Pass/Fail |
|-----------|--------------|------------|------------------------|---------------|---------------------------|-----------|
| 9 (Left)  | Dry Then Wet | Dry        | Forward Heel Slip      | 1.16          | Min. 0.40                 | Pass      |
|           |              |            | Backward Forepart Slip | 1.09          | Min. 0.40                 | Pass      |
|           |              | Wet        | Forward Heel Slip      | 0.74          | Min. 0.40                 | Pass      |
|           |              |            | Backward Forepart Slip | 0.74          | Min. 0.40                 | Pass      |
| 9 (Right) | Wet Then Dry | Wet        | Forward Heel Slip      | 0.65          | Min. 0.40                 | Pass      |
|           |              |            | Backward Forepart Slip | 0.72          | Min. 0.40                 | Pass      |
|           |              | Dry        | Forward Heel Slip      | 1.05          | Min. 0.40                 | Pass      |
|           |              |            | Backward Forepart Slip | 1.03          | Min. 0.40                 | Pass      |
| 9 (Right) | Dry Then Wet | Dry        | Forward Heel Slip      | 1.01          | Min. 0.40                 | Pass      |
|           |              |            | Backward Forepart Slip | 0.96          | Min. 0.40                 | Pass      |
|           |              | Wet        | Forward Heel Slip      | 0.62          | Min. 0.40                 | Pass      |
|           |              |            | Backward Forepart Slip | 0.63          | Min. 0.40                 | Pass      |
| 9 (Left)  | Oily Wet (#) |            | Forward Heel Slip      | 0.33          | Min. 0.33                 | Pass      |
|           |              |            | Backward Forepart Slip | 0.36          | Min. 0.33                 | Pass      |
| 9 (Right) |              |            | Forward Heel Slip      | 0.35          | Min. 0.33                 | Pass      |
|           |              |            | Backward Forepart Slip | 0.34          | Min. 0.33                 | Pass      |
| 9 (Right) |              |            | Forward Heel Slip      | 0.35          | Min. 0.33                 | Pass      |
|           |              |            | Backward Forepart Slip | 0.34          | Min. 0.33                 | Pass      |

Remark: # = 0.2±0.02 g (Approximately 8 Drops) Of Corn Oil With Distilled Water

Note: It Must Be Noted That The Slip Resistance Test Carried Out In This Report Denotes An Indication Of Slip Of This Particular Footwear/Component On The Surface Mentioned In The Test Item. It Is Important To Note That Footwear Is Subjected To Many Different Conditions Encountered In Everyday Use And That It Is Impossible To Make Footwear Resistant To Slip In All Conditions. Nevertheless, It Is Generally Accepted That Problems Are Minimized If The Guideline Coefficients Of Friction Are Achieved.



Total Quality. Assured.

TEST REPORT

Tests Conducted (As Requested By The Applicant)



中国认可  
国际互认  
检测  
TESTING  
CNAS L0220

Number: GZHT91332070



/ lynnyang

Page 3 Of 5

**Intertek Testing Services Shenzhen Ltd. Guangzhou Branch**  
深圳天祥质量技术服务有限公司广州分公司  
Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou 510730  
广州市黄埔区保盈东路8号401房、501房、601房、801房、901房、1003房  
Tel: +86 20 2820 9114 Postcode: 510730

[www.intertek.com](http://www.intertek.com)

检验检测专用章  
SHENZHEN  
BRANCH  
(6)







End Of Report

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.*

**Remark:**

1. As Requested by the Applicant, For Details Refer to Attached Page (S).
2. All the tested item are tested under the standard condition.
3. The report is valid with commission test only for the test samples in the case of delivering samples by clients.