



Total Quality. Assured.
TEST REPORT



中国认可
国际互认
检测
TESTING
CNAS L0220

Number: GZHT90881362

Date: Apr 24, 2019

Applicant: CORTINA N.V.
MEERSBLOEM-MELDEN 42,
9700 OUDENAARDE,BELGIUM
Attn: PETER DE MEZURE

Sample Description:

One and a half (1.5) pairs of submitted samples said to be Steel plates.

Standard	: ASTM F2413-18
Size	: US 9
Buyer's Name	: CORTINA N.V.
Ref. No	: DOLCE81,GUSTO81,LUNGO81,ROMA81,VOLLUTO81
Brand	: SAFETYJOGGER
Manufacturer	: CORTINA N.V.
Colour	: BLACK
Vendor	: --
Supplier	: --
P.O. No.	: --
Ref.	: Steel plate used for Men Casual Low Safety with M2329 PU/RUBBER sole
Country Of Origin	: --
Goods Exported To	: Belgium/U.S.A.
Date Received/Date Test Started:	Apr. 17, 2019
Date Final Information Confirmed:	--

Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Guiliang Dong
Senior Lab Manager



/ kayyu

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

Room 02, 1-8/F. & Room 01, E101/E201/E301/E401/E501/E601/E701/E801,
No.7-2, Caipin Road, Guangzhou Science City, GETDD, Guangzhou, Guangdong, China
广州经济技术开发区科学城彩频路7号之二第1-8层02房、01房101、
E201、E301、E401、E501、E601、E701、E801
Tel: +86 208213 9001 Fax: +86 20 82089909 Postcode: 510663

3/F., Hengyun Building, 235 Kaifa Ave., Guangzhou
Economic & Technological Development District, Guangzhou,
China
中国广州经济技术开发区开发大道235号恒运大厦3楼
Tel: +86 20 83966868 Fax: +86 20 82228169 Postcode: 510730



Total Quality. Assured.

TEST REPORT

Tests Conducted (As Requested By The Applicant)



中国认可
国际互认
检测
TESTING
CNAS L0220

Number: GZHT90881362

Flex Resistance For Puncture Resistant Devices (ASTM F2412-18a, 11.7 & CSA Z195-14, 6.3.2)

		<u>ASTM F2413-18</u> <u>Requirement</u>	<u>Pass/Fail</u>
Left:	No Signs Of Cracking After 1.5×10^6 Flexes.	*	Pass
Left:	No Signs Of Cracking After 1.5×10^6 Flexes.	*	Pass
Right:	No Signs Of Cracking After 1.5×10^6 Flexes.	*	Pass


Remark: * = No Signs Of De-lamination Of Layers Or Cracking After 1.5×10^6 Flexes.

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

深圳天祥质量技术服务有限公司广州分公司

Room 02, 1-8/F. & Room 01, E101/E201/E301/E401/E501/E601/E701/E801,
No.7-2, Caipin Road, Guangzhou Science City, GETDD, Guangzhou, Guangdong, China
广州经济技术开发区科学城彩频路7号之二第1-8层02房、01房101、
E201、E301、E401、E501、E601、E701、E801
Tel: +86 208213 9001 Fax: +86 20 82089909 Postcode: 510663

3/F., Hengyun Building, 235 Kaifa Ave., Guangzhou
Economic & Technological Development District, Guangzhou,
China
中国广州经济技术开发区开发大道235号恒运大厦3楼
Tel: +86 20 83966868 Fax: +86 20 82228169 Postcode: 510730



End Of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.