

Medium


MODULO S3S LOW

MODULOS3L

#####

```
##### MODULO# ##### # # ##### # # # # # #  
### ## #, ### ##, ### ##, ESD, ## ##, ## # # ## # #  
#####. ## ## #####.
```

## ##	#####
## ##	##
###	SJ # ##
##	## ## #
###	### PU/### PU
Top	## ##
#####	S3S / SR, SC, ESD, CI, FO
## ##	EU 35-50 / UK 3.0-14.0 / US 3.0-15.0 JPN 21.5-33.0 / KOR 230-330
## ##	0.536 kg
###	ASTM F2413:2018 EN ISO 20345:2022+A1:2024 IS 15298 (Part 2): 2016



```
## ##
### ## ##### ##### ## #####
#####. ## ## ##### ## ## #
##### ## ##### ## #####.
```



##.



```
### ##(SR)
### ##### SRA+SRB=SRC ###
#####. SR# ### ##### ### ###
## ## ##### #####.

```



```
### ##
ESD# ## ### ##### # ## ###
##### ### ##### ##### ## ##
### #####. ## ### 100#####
100### #####.
```



```
### #(SC)
### # # # ## ### ## ##
##### ## ## ## ## ##
##### ## #####.
```



```
## ## ##
### ## ## ##### ## ## ##.
### ## ## 100% ## ## #####
#####.
```



GRY



BLK



112



AH7

##:
####, ###, ##, ##, ####, ##

##:
##, ## #### ##, ## ##

##:
####.

	##	## ##	##	EN ISO 20345
## ##	#####			
	##: ### ##	mg/cm²/h	8.20	≥ 0.8
	##: ### ##	mg/cm²	68	≥ 15
## ##	##			
	##: ### ##	mg/cm²/h	60.62	≥ 2
	##: ### ##	mg/cm²	485	≥ 20
###	SJ # ##			
	###: ####(##/##)(###)	##	Dry 25600 cycles/Wet 12800 cycles	25600/12800
###	### PU/### PU			
	### ####(## ##)	mm³	127mm³ (Density:1.09g/cm³)	≤ 150
	## ## ## - ## + NaLS - ## ## ##	##	0.33	≥ 0.31
	## ## ## - ## + NaLS - ## ## ##	##	0.42	≥ 0.36
	SR ## ## - ## + #### - #### ## ##	##	0.22	≥ 0.19
	SR ## ## - ## + #### - ## ## ##	##	0.25	≥ 0.22
	### ## #	###	31.5	0.1 - 1000
	ESD #	###	21	0.1 - 100
	#### ## ##	J	31	≥ 20
Top	## ##			
	#### ## # (## # #### 100J)	mm	N/A	N/A
	#### ## # (## # ## ## 10kN)	mm	N/A	N/A
	#### ## # (## # ## ## 200J)	mm	15.5	≥ 14
	#### ## # (## # ## ## 15kN)	mm	21.0	≥ 14

#: 42
##, ## ## #### ## # ####. ## #### ## Safety Jogger # #### ##, ### ## ## ## ## #### #### ## # ####.

